



METZ 33EN-TG

EPOXY NOVOLAC

CORROSION RESISTANT EPOXY TOPPING



DESCRIPTION:

Metz 33EN-TG Epoxy Novolac is a 100% solids trowel applied monolithic topping, based on special resins and hardeners which impart outstanding chemical resistance, especially against concentrated inorganic acids. It also cures rapidly even at low temperatures, thus minimising downtime. Use Metz 33EN-VG Epoxy Novolac for coves and vertical surfaces.

FEATURES AND BENEFITS:

- **Outstanding Chemical Resistance**
Resistant to a wide range of concentrated acids and alkalis, solvents, oils and fats, Resistant to spillages of concentrated sulphuric, hydrochloric and phosphoric acids. Refer Metz Chemical Resistance Chart.
- **High Temperature Resistance**
- **High bond, tensile and compressive strengths**
- **Solventless**
100% solids formulation.
- **Rapid Cure**
Fast setting, minimises downtime.
- **Low Temperature Cure**
Cures at temperatures down to 0°C
- **Can be laid by conventional hand trowel or power trowel methods**

RECOMMENDED:

As a monolithic topping to protect concrete against chemical and mechanical attack in:

- Secondary containment linings
- Acid plants
- Oil refineries
- Steel Mills
- Food processing plants
- Meat and Poultry plants
- C.I.P. rooms in food and beverage plants

NOT RECOMMENDED:

- For exposure to some strong organic acids and solvents. Refer Metz 93PU-TG and Metz Chemical Resistance Chart.

PHYSICAL PROPERTIES:

	(Typical Values)
Density:	2.0 - 2.2 g/cm ³
Compressive Strength:	100 MPa
Adhesion to concrete (ASTM C1583):	>1.5MPa (concrete failure)
Flexural Strength:	35 MPa
Maximum Service Temperature, per °C:	150
Coefficient of Thermal Expansion, per °C:	40 x 10 ⁻⁶
Colour:	Colour changes may occur upon ageing, exposure to U.V. light or strong chemicals

COVERAGE: Theoretical quantities (allow for wastage)

Metz Epoxy Primer	0.21 kgs per sq metre at 0.2mm thickness
Metz 33EN-TG Epoxy Novolac	12.6 kgs per sq metre at 6mm thickness
Metz 33EN-Sealer (if required)	0.25 kgs per sq metre (depending on surface finish)

APPLICATION TEMPERATURE:

For optimum results, maintain a temperature of 5°C to 40°C on air and substrate and components during mixing, application and curing.

Note: Materials should be kept as cool as possible. Reducing material temperature will increase pot life.



Acid Proofing & Industrial Flooring • Specialty Ceramic Tiles





METZ 33EN-TG

EPOXY NOVOLAC

CORROSION RESISTANT EPOXY TOPPING



INSTRUCTIONS FOR USE

1. Temperature of Working Area

For optimum results, maintain a temperature of 5°C to 40°C on air and substrate and components during application and curing.

At temperatures below 5°C, the application becomes more difficult and curing is retarded.

At temperatures above 40°C, the working time decreases.

Application in direct sunlight and rising surface temperatures may result in blistering of the coating due to expansion of entrapped air or moisture in the substrate. Note: At ambient temperatures below 15°C, the liquid should be warmed to 20-25 °C prior to use.

2. Surface Preparation

All surfaces must be clean, dry and free from oil, grease, water and other contaminants which may inhibit bond. Remove all standing water. For best results surfaces should be dry. Concrete on grade should utilise a waterproof barrier beneath the slab.

(i) New Concrete

New concrete should have attained a compressive strength of 20 MPa minimum. Surface must be free from laitance, form oils and curing compounds. The surface should have a fine wood floated or lightly broomed finish and be 28 days old. Abrasive blast or high-pressure water blast to remove laitance and provide a uniform, textured surface. Surface moisture content should be less than 10%.

(ii) Old Concrete

Concrete must be sound. Remove laitance, old paints, protective coatings and attacked or deteriorated concrete.

Chemically clean surface to remove any contaminants.

Abrasive blast or high-pressure water blast to remove laitance and provide a uniform, textured surface.

All structural cracks should be repaired and all slopes reestablished with approved repair material (e.g. Metz 10 or Metz 10EN Epoxy Concretes).

All prepared surfaces must be vacuumed to remove any loose deposits and contamination.

(iii) Edge Detail

Where ever an exposed edge of the material occurs, (e.g. in doorways) an anchoring groove at least 9mm deep should be cut in the substrate. Consult Metz for full details.

3. Mixing

a) Mixing Equipment

Mechanical mixing is required. A special resinous cements mixer or mortar mixer is suitable.

Smaller quantities can be mixed using a heavy duty slow speed drill with a suitable paddle. Consult Metz for details.

b) Mixing Proportions

Metz Epoxy Primer	By Weight	By Volume
Liquid	1.85	1.6
Hardener	1	1
Metz 33EN-TG	By Weight	By Volume
Liquid L2	2	2.1 litres
33EN Hardener	1	1.15 litres
33EN-TG Powder	16	20kg (1 bag)

Note: The liquid to hardener ratios must not be altered under any circumstances

The powder proportion can be altered by up to 10% to suit conditions. The addition of extra powder may result in a more porous surface.

c) Mixing Procedure

Remix liquids prior to use.

For Metz Epoxy Primer:

Mix liquid and hardener together thoroughly for 1-2 minutes.

For Metz 33EN-TG:

Mix liquid and hardener together thoroughly for 1 - 2 minutes.

Add powder gradually with constant stirring. Mix for 3 - 5 minutes.

At the end of the mixing period, all material should be wetted out and uniform in colour and consistency. Material which has begun to set must be discarded. Do not add any solvent, additive or adulterant to any component or to the mixed material.

d) Pot Life

Metz Epoxy Primer	Metz 33EN-TG
at 20°C 70 minutes	at 20°C 40 minutes
at 30°C 40 minutes	at 30°C 30 minutes
at 40°C 30 minutes	at 40°C 20 minutes

Note: Increase in temperature will decrease pot life, as will leaving mixed material in a large mass. Spread out material in a thin layer as soon as possible after mixing.

e) Clean Up

Mixing equipment, tools, etc., can be cleaned with Metz Cleaner, xylene, acetone or MEK prior to initial set of cement.

Note: Ensure you have the latest mixing instructions, refer www.metz.net.au for most current data sheet version.

4. Installation

(i) Metz Epoxy Primer

Apply to concrete using squeegee then back-roll with short nap roller. Metz 33EN-TG Epoxy Novolac can be placed immediately after the application of the primer, and must be placed whilst the primer is still tacky. If the primer has hardened, consult Metz. Do not apply Metz 33EN-TG Epoxy Novolac topping.

(ii) Metz 33EN-TG

Material should be placed immediately after mixing. Do not let the mixed material remain in mixing vessel. Spread Metz 33EN-TG with screedbox, screed or by hand to desired thickness (nominally 6mm). Use steel float to compact and finish surface. Finishing must be completed within the pot life of the material. Consult Metz for screedbox and power trowel directions.

For added protection it is possible to topcoat with Metz33EN-Sealer - refer data sheet for details.

5. Setting/Curing:

Setting Time	Full Cure
at 20°C 6 hours	at 20°C 3 days
at 30°C 4 hours	at 30°C 2 days
at 40°C 3 hours	at 40°C 2 days

Do not allow water, chemicals or traffic on the material surface for a minimum of 24 hours. For harsh chemical or physical environments, cure a minimum of 72 hours at 20°C prior to exposure.

6. Storage

Store in original containers in cool dry place. Under these conditions minimum shelf life is 12 months.

7. Safety Precautions

Liquid and Hardener

Use chemical goggles, PVC gloves and barrier cream.

Avoid contact with skin and eyes.

Powder

Avoid breathing dust. Ensure adequate ventilation.

For full safety precautions refer to Material Safety Data Sheets for all components.

- The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
- If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - Metz shall not be liable for any loss or damage including consequential loss or damage or loss of profits arising thereby;
 - Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.

REV 05/09

METZ SPECIALTY MATERIALS PTY LTD

A.C.N. 140 636 639

15A Stanton Road, Seven Hills, NSW 2147
Facsimile: (02) 9671 4292 Phone: (02) 9671 1311

6 University Place, Clayton North, VIC 3168
Facsimile: (03) 9561 6944 Phone: (03) 9561 6144

Unit 16, 42 Smith Street, Capalaba QLD 4157
Facsimile: (07) 3823 5552 Phone: (07) 3823 5555

Exclusive Distributor:

REZAYAT PROTECTION COATINGS COMPANY LTD.

P.O Box 90, Al-Khobar 31952

Kingdom of Saudi Arabia

Tel: +966-3-882 5700 Exts. 4001 and 4052

Fax: +966-3-882 6716